

# Technical Data Sheet **GEHR® PE-UHMW-ELS**

Physical Properties	Test Method	Unit	Value
Specific Gravity	ISO 1183	g/cm <sup>3</sup>	0,93
Water Absorption	ISO 62	%	0
Humidity Absorption	ISO 62	%	0,01
Maximum Permissible Service Temperature	UL746B	°C	90

Mechanical Properties	Test Method	Unit	Value
Tensile Strength at Yield	ISO 527	MPa	> 17
Elongation at Yield	ISO 527	%	20
Tensile Strength at Break	ISO 527	MPa	≥ 40
Elongation at Break	ISO 527	%	≥ 50
Impact Strength	ISO 179	kJ/m <sup>2</sup>	n.B.
Notch Impact Strength	ISO 179	kJ/m <sup>2</sup>	n.B.
Ball Indentation Hardness / Rockwell	ISO 2039	MPa	38 / -
Shore Hardness, 3 sec value	ISO 868	Scale D	63
Tensile Modulus	ISO 527	MPa	680
Static friction / Sliding friction against steel	DIN 53375	MPa	0,15 / 0,1-0,15

Thermal Properties	Test Method	Unit	Value
Vicat Softening Temperature (VST/B/50)	ISO 306/B	°C	79
(VST/A/50)	ISO 306	°C	-
Heat Deflection Temperature (HDT/B)	ISO 75	°C	-
(HDT/A)	ISO 75	°C	-
Coefficient of Linear Thermal Expansion	ISO 11359	K <sup>-1</sup> *10 <sup>-4</sup>	2
Thermal Conductivity from 20 to 80°C	DIN 52612	W/(m*K)	0,41
Glass Transition Temperature	ISO 3146	°C	-
Melt Temperature	ISO 3146	°C	130-135

Electrical Properties	Test Method	Unit	Value
Volume Resistivity	VDE 0303/3	Ω*cm	< 10 <sup>6</sup>
Surface Resistivity	VDE 0303/3	Ω	< 10 <sup>6</sup>
Dielectric Constant at 1 MHz	IEC 60250	-	-
Dielectric loss factor at 1 MHz	IEC 60250	-	-
Dielectric Strength	IEC 60243-1	kV/mm	-
Tracking Resistance	IEC 60112	V	-

Additional Data	Test Method	Unit	Value
Bondability	-	-	-
Physiological Safety	EEC FDA	- -	- -
Flammability	UL 94	-	-
Limiting Oxygen Index (LOI)	ASTM D2863	%	-

These values have been generated by qualified parties and contain our current experience. They can therefore be described as applicable to a high degree, without being mandatory for every case of application. The values given are average values which are verified by systematic tests. The characteristic values correspond to the specifications of DIN EN 15860 and may vary on the finished product. These are guide values and not guaranteed properties which are only intended to provide information about our products and to assist in the selection of materials. In case of missing measured values, raw material data or literature values were used, if available. Subject to change.

n.B. = no Break

+ = Yes

o = Limited

- = No / No Data Available